

Promat



CAFCO[®] Plastic Coated Galvanised Mesh & CAFCO[®] Helical CD Weld Pin

Reinforcement System



CAFCO® Plastic Coated Galvanised Mesh & CAFCO® Helical CD Weld Pin

Reinforcement System

INTRODUCTION – CAFCO® Plastic Coated Galvanised Mesh

CAFCO® Plastic Coated Galvanised Mesh is a hexagonal mesh wire netting “reverse twist”, galvanised after weaving and coated in blue plastic.


This netting is embedded in the fire protection coating.

Nominal wire diameter (d) is the diameter in mm to designate the wire.

Real wire diameter is the arithmetical mean of the minimum and maximum diameter, measured in the same section of a straight piece of wire by mean of the minimum and maximum diameter.

Nominal mesh size is the distance in mm to designate the mesh.

Real mesh size (a) is the distance in mm between the twists.



Raw material		
Chemical composition of wire rod	Element	%
	C	0.10
	Si	0.30
	Mn	0.50
	P	0.070
	S	0.060
Zinc slabs	Minimum 99.5% of pure zinc	
Plastic coating	Polyvinyl chloride (PVC), turquoise blue in accordance with RAL code 5012 or Munsell code 10 BG 6/6.	

Properties and performance		
Wire diameters and tolerances	Nominal diameter (d)	1.00mm or 1.50mm
	Core diameter	1.00mm ± 0.065mm in accordance with DIN 177
	Final diameter	1.50mm ± 0.10mm in accordance with DIN 3036 T2
Mesh sizes and tolerances	50mm ± 6mm in accordance with DIN 1200. The actual mesh size is the average value of 10 successive mesh openings in the transverse direction of the netting. Actual mesh size in mm = $L/10 - 2d$ “L” being the length in mm of 10 successive meshes in the transverse direction. “d” being the wire diameter in mm.	
Tensile strength (Rm) of the wires	350-500N/mm ²	
Mass of zinc	Minimum mass of zinc is 35g/m ² in accordance with DIN 1200. To be determined by double weighing on a piece of netting of 150mm x 150mm without salvage and to be expressed in g/m ² of the wire surface.	
PVC coating	Homogeneous coating free from uncoated spots.	

QUALITY ASSURANCE

Promat manufactures to a quality system in accordance with ISO 9001:2000 and has received full accreditation to these standards.

Operating to these standards means that all activities, which have a bearing upon quality, are set out in written procedures. Systematic and thorough checks are made on all materials and their usage. Test equipment is subjected to regular checks and is referred back to national standards.

The information given in this data sheet is based on actual tests and is believed to be typical of the product. No guarantee of results is implied however, since conditions of use are beyond our control.



CAFCO® Plastic Coated Galvanised Mesh & CAFCO® Helical CD Weld Pin

Reinforcement System

PACKAGING – CAFCO® Plastic Coated Galvanised Mesh

23 rolls strapped on wooden pallet under stretch-foil, each roll is shrink-packed.

Packaging reference	
Roll length	25m ± 2%
Netting width	Nominal 1000mm ± 30mm in accordance with DIN 1200
Inside diameter of the rolls	Approximately 100mm
Outside diameter of the rolls	Approximately 210mm
Roll weight	8.2kg ± 5%
Identification	Each roll is provided with a coloured identification tag

INTRODUCTION – CAFCO® Helical CD Weld Pin

CAFCO® Helical CD Welded Pins are special stainless steel pins welded to the substrate using an approved capacitance discharge weld machine incorporating a special Cafco supplied chuck.

The helical pins are used to retain the plastic coated galvanised retention/reinforcement mesh used in conjunction with the Cafco FENDOLITE® MII system.

No clips are required.

Properties and performance	
Material	Stainless steel in accordance with AISI.316.S.11
Dimensions	Wire diameter: 2.20mm ± 0.01mm Headed flange diameter: 4.72mm ± 0.03mm Headed flange thickness: 0.079mm ± 0.02mm
Tensile strength	Minimum 540N/mm ²

HEALTH AND SAFETY

The use of eye protection and gloves is recommended. In addition, appropriate face masks should be used during any drilling operations.

Size and shape of the product would generally preclude ingestion. Medical attention should be sought in the event of parts being swallowed.

Normal hygiene precautions should be followed by washing hands before handling or eating food.

Promat activities are conducted with due regard to all statutory requirements with appropriate safeguards against exposing employees and the public to health and safety risks.



For latest information of the Promat Asia Pacific organisation, please refer to www.promat-ap.com

ASIA PACIFIC HEADQUARTERS

Promat International (Asia Pacific) Ltd.
Unit 19-02-01, Level 2 PNB Damansara
No.19 Lorong Dungun, Damansara Heights
50490 Kuala Lumpur
MALAYSIA
Tel: +60 (3) 2095 5111
Fax: +60 (3) 2095 6111
Email: spraysinfo@promat-ap.com

AUSTRALIA

Promat Australia Pty. Ltd.
1 Scotland Road
Mile End South, SA 5031
Tel: 1800 PROMAT (776 628)
Fax: +61 (8) 8352 1014
Email: spraysinfo@promat.com.au

New South Wales Office **Promat Australia Pty. Ltd.**

Unit 1, 175 Briens Road
Northmead, NSW 2152
Tel: 1800 PROMAT (776 628)
Fax: +61 (2) 9630 0258
Email: spraysinfo@promat.com.au

Victoria Office

Promat Australia Pty. Ltd.
3/273 Williamstown Road
Port Melbourne, VIC 3207
Tel: 1800 PROMAT (776 628)
Fax: +61 (3) 9645 3844
Email: spraysinfo@promat.com.au

Queensland Office

Promat Australia Pty. Ltd.
Unit 2 Level 1
49 Gregory Tce
Spring Hill, QLD 4000
Tel: 1800 011 376
Fax: 1800 334 598
Email: spraysinfo@promat.com.au

CHINA

Promat China Ltd.
Room 503, Block B, Qi Lin Plaza
13-35 Pan Fu Road
510180 Guangzhou
Tel: +86 (20) 8136 1167
Fax: +86 (20) 8136 1372
Email: spraysinfo@promat-ap.com

Beijing Office

Promat North China
(Division of Promat China Ltd.)
Room 1507 Building 5, SOHO Xiandaicheng
No.88 Jianguo Road, Chaoyang District
100022 Beijing
Tel: +86 (10) 8589 1254
Fax: +86 (10) 8589 2904
Email: spraysinfo@promat-ap.com

For Promat International groups worldwide:
www.promat-international.com

1. This document is produced on the basis of information and experience available at the time of preparation. Promat is constantly reviewing and updating all of its test data and reserves the right to change products and specifications without notice.
2. Promat is not responsible if recipients of fire test reports, assessments or literature incorrectly interpret said contents and use products based on those interpretations.

HONG KONG

Promat International (Asia Pacific) Ltd.
Room 1010, C.C. Wu Building
302-308 Hennessy Road
Wanchai
Tel: +852 2836 3692
Fax: +852 2834 4313
Email: spraysinfo@promat-ap.com

INDIA

Promat International (Asia Pacific) Ltd.
(India Representative Office)
610-611, Ansal Imperial Tower
C-Block, Community Centre
Naraina Vihar, Naraina
110028 New Delhi
Tel: +91 (11) 2577 8413
Fax: +91 (11) 2577 8414
Email: spraysinfo@promat-ap.com

Bangalore Office

Promat International (Asia Pacific) Ltd.
(India Representative Office)
Cabin No.BC-9 & BC-10
Oculus Workspaces, No.66/1, 2nd Floor
Coles Road, Frazer Town
560005 Bangalore
Tel: +91 (80) 4031 4151
Fax: +91 (80) 4125 2135
Email: spraysinfo@promat-ap.com

Mumbai Office

Promat International (Asia Pacific) Ltd.
(India Representative Office)
Stylus Serviced Offices
Ground Floor, Velocity
Phase 1, Logitech Park
Andheri Kurla Road, Andheri East
400072 Mumbai
Tel: +91 (22) 6769 4567
Fax: +91 (22) 6769 4568
Email: spraysinfo@promat-ap.com

MALAYSIA

Promat (Malaysia) Sdn. Bhd.
Unit 19-02-01, Level 2 PNB Damansara
No.19 Lorong Dungun, Damansara Heights
50490 Kuala Lumpur
Tel: +60 (3) 2095 8555
Fax: +60 (3) 2095 2111
Email: spraysinfo@promat-ap.com

SINGAPORE

Promat Building System Pte. Ltd.
10 Science Park Road, #03-14 The Alpha,
Singapore Science Park II
Singapore 117684
Tel: +65 6776 7635
Fax: +65 6776 7624
Email: spraysinfo@promat-ap.com

Your local Promat supplier

